

PACO Screen-Printing-Meshes PACO ED-Qualitäten (extra dünn) / *PACO ED-Qualities (extra thin)*

No. of Mesh	PACO-Code	Opening		Wire Diameter		Open Area (%)	Weight (kg/m ²)	Thickness (µm)	Standard-thickness (µm) +/- 1 µ	Theor. Ink.-vol. (Cm ³ /m ²)	Cal. MD (25-30%) (µm) +/- 1 µ	Theor. Ink.-vol. (Cm ³ /m ²)
		(µm)	(inches)	(mm)	(inches)							
40 L	ED 76/560	0,560	.022	0,076	.0028	77,0	0,12	160-170	165	127,9	115	89,1
60 L	ED 50/370	0,370	.0145	0,050	.0020	76,0	0,08	110-125	118	91,8	75	58,3
70 L	ED 65/300	0,300	.0118	0,065	.0026	68,0	0,15	130-145	138	93,0	98	66,0
80 L	ED 50/265	0,265	.0104	0,050	.0020	71,0	0,10	110-120	115	81,6	75	53,2
165 L	ED 35/118	0,118	.0046	0,035	.0014	59,0	0,11	80 - 95	88	52,5	54	32,2
200 L	ED 35/ 92	0,092	.0036	0,035	.0014	52,0	0,13	75 - 90	84	44,1	63	28,9
230 L	ED 30/ 80	0,080	.00315	0,030	.0012	53,0	0,10	63- 70	67	35,5	46	24,4
280 L	ED 25/ 65	0,065	.00256	0,025	.0010	52,0	0,09	54 - 64	69	36,2	38	19,9
325 L	ED 23/ 55	0,055	.00216	0,023	.0009	50,0	0,09	50 - 60	55	27,4	36	17,9
350 L	ED 20/ 52	0,052	.0020	0,020	.00078	52,0	0,08	42 - 52	47	24,7	33	17,3
370 L	ED 23/ 46	0,046	.0018	0,023	.0009	44,0	0,10	50 - 60	55	24,3	37	16,4
400 L	ED 18/ 45	0,045	.00178	0,018	.0007	51,0	0,07	42 - 52	47	24,1	33	16,9
400 L	ED 23/ 40	0,040	.0016	0,023	.0009	41,0	0,11	50 - 60	55	22,4	37	15,1
500 L	ED 20/ 30	0,030	.0012	0,020	.00078	36,0	0,11	46 - 52	49	18,0	36	13,2